



Latex Bonding Agents

SEPTEMBER 2011

SELECTION CRITERIA					
USE		APPLICABLE STANDARDS	STRENGTH REQUIREMENTS		LAMBERT PRODUCT
			TENSILE	BOND	
Plaster Applications	Interior	ASTM C-631	20-lbs. Minimum		Hibond
	Exterior	ASTM C-932	150-lbs. minimum		Acrylbond
	Both	ASTM C-932	150-lbs. Minimum		932 LINK™
	Interior	N/A	N/A	N/A	Lambco Bond
Concrete Applications	Both	ASTM C-1059		1250-lb. minimum	932 LINK™
	Interior	ASTM C-1059, Type I		400-lb. minimum	Hibond or PVA-20
	Exterior	ASTM C-1059, Type II		1250-lb. minimum	Acrylbond
	Interior	N/A	N/A	N/A	Lambco Bond

COMPARISON				
PRODUCT	RESIN	PROPERTIES	USES	LOCATIONS
932 LINK™	VAE	Non-rewettable	Concrete & plaster bonding agent & admix	Exterior & interior
Acrylbond	Acrylic	Non-rewettable	Concrete & plaster bonding agent & admix	Exterior & interior
Hibond	PVA	Rewettable	Portland cement plaster and some concrete work	Interior & protected exterior
PVA-20	PVA	Rewettable	Portland cement plaster	Interior
Lambco Bond	PVA	Rewettable	Portland cement plaster	Interior
L-16 Primer	EVA	Rewettable 1-time	Only for L-16 Self-Level Underlayment	Exterior & interior

20 North Coburn Avenue ~ Orlando, FL 32805-2198 ~ (407) 841-2940 ~ fax (407) 839-1890 ~ (800) 432-4746

LAMBERT CORPORATION