



Product Description

EPIWELD[®] 580 is a solvent-free, gray colored epoxy adhesive, binder, and mortar for concrete, masonry and steel. It is a medium viscosity moisture insensitive epoxy conforming to ASTM C-881. **EPIWELD[®] 580** has a high modulus of elasticity that allows structural bonding to dry and damp concrete surfaces that are free of standing water or hydrostatic pressure. When used as an epoxy mortar, **EPIWELD[®] 580** accepts good aggregate loading without appreciable strength reductions.

EPIWELD[®] 580 was primarily designed to be used as a bonding agent for new, fresh concrete being placed on or to structurally sound (cured) hardened concrete. It soon found additional usage as a structural adhesive for bonding masonry, metal, ceramic, and wood materials. It has been used successfully as a base coating for aggregates cast on concrete for non-skid ramps. Grouting bolts, dowels, pins, etc. are also some of the common uses of **EPIWELD[®] 580**.

Installation

Before using this product, please refer to the Material Safety Data Sheet for additional information. Proper handling precautions MUST be followed. The conditions of use, handling, and application of this product and information (whether verbal or written), including any suggested formulations and recommendations, are beyond Lambert Corporation's control. Therefore, it is imperative that testing be performed to determine satisfaction and suitability for intended use and health, safety, and environmental issues. The following information is meant as a guideline of best industry practices. While Lambert Corporation does suggest adherence to these guidelines, unforeseeable variables and/or developed successful installer practices may cause variation in methods and/or results.

Surface Preparation-Concrete

The success of any application is directly proportional to the completeness of substrate preparation and the care in application. Surfaces must be clean and structurally sound. All concrete surfaces to be bonded, coated or repaired should be dry, however a slightly damp, surface-dry condition is acceptable. Tests areas are required when this condition exists. Mechanical scarifying to remove laitance and expose sound, coarse aggregate will result in optimum bond. Non-porous, dense or glassy type concrete surfaces must be etched with a solution (10%) of muriatic acid. New concrete needs to be aged/cured before an epoxy is applied (generally 28 days or more).

Surface Preparation-Steel

Exposed rebar, anchor bolts, etc. to be bonded must be free of rust, paint, oil, and dirt. Metals should be sanded or sandblasted to a commercial blast finish. If mechanical cleaning is impractical, chemical cleaning should be used. Clean, dry, lightly abraded surfaces give a better mechanical key/bond.

Mixing

The individual components of **EPIWELD[®] 580** should be thoroughly stirred before the two are mixed together. The resin (part-A) and hardener (part-B) should then be mixed in the proper ratio (1 part resin (A) to 1 part (B) by volume) for 3 to 5 minutes resulting in a homogenous and uniformly gray colored material. It is recommended that a slow speed drill (600-RPM maximum) and paint paddle or a "jiffy" mixer be used for mixing. Hand mixing with paint paddle is also acceptable but a uniform gray color must be achieved. **EPIWELD[®] 580** is designed for application both neat and as a grout or mortar. Proportion of aggregate to 1 part mixed epoxy varies with proposed end use. 2 to 3 parts aggregate to 1 part mixed **EPIWELD 580** is a good general recommendation.

Cautions

Due to many variables in bonding to damp or dry surfaces, be certain to test application under the same conditions as the full-scale work. When bonding to damp or slightly wet surfaces, test if dampness or moisture is caused by hydrostatic pressure. Moisture passing through the substrate by pressure during application and curing of epoxy will cause bond failures.

Limitations

Aggregate must be oven dried to avoid encapsulation of moisture. Condition components to 60-70°F (15.5-21.1°C) prior to use. Epoxies stored below 60°F (15.5°C) will cause the epoxy to thicken substantially making it difficult to blend the two materials and obtain a proper mating of resin and hardener. Pot life of mixed **EPIWELD** at 70°F (21.1°C) is about 30 minutes. Pot life is dependent upon material temperature and quantity catalyzed. The greater the mass, the shorter the pot life. Increased mass and temperature result in higher exothermic and shorter pot life. Higher temperatures decrease pot life; lower temperatures and the addition of aggregate lengthen pot life. Temperatures of substrate will have similar results on pot life.

Application - EPIWELD[®] 580 can be applied by brush, squeegee, trowel, roller. Spray application is difficult.

Bonding Fresh Concrete to Hardened Concrete

Make sure sufficient coating of **EPIWELD[®] 580** is applied to the surface to coat all voids and crevices. Only an area of which fresh concrete will be placed within the cure time should be coated. If **EPIWELD[®] 580** sets before the fresh concrete is placed, it may require removal. If poorly bonded. Under certain conditions recoating may be acceptable. The epoxy must be tacky when fresh concrete is poured to it. Porous concrete may absorb **EPIWELD[®] 580** and leave surface dry. A prime coat may be needed in this case. Thickness of topping or patch should be sufficient to maintain its own structural strength. **EPIWELD[®] 580** prevents migration of water from the new slab into the old concrete thus producing a stronger concrete. **EPIWELD[®] 580** also becomes a moisture barrier preventing subsurface water coming through the concrete.

Bonding Hardened Concrete to Hardened Concrete

Brush coat each of the mating surfaces with a liberal amount of **EPIWELD[®] 580**. Allow 10 minutes for penetration. It is important that the epoxy be tacky when mating surfaces are placed together. Bonded parts should be left undisturbed for at least 24 hours. Support pressure may be required during cure time.

	<p>Packaging:</p> <p>2 gal-Total Unit (7.6L) 1 gal (3.8L) per Part A and Part B</p> <p>½ gal-Total Unit (1.9L) 1 quart (0.95L) per Part A and Part B</p>
--	---



EPOXY PRODUCTS

EPIWELD® 580

MASTER FORMAT: 03 31 20

Binder for Epoxy Aggregate Grout, Mortar, Concrete

To produce a sand filled grout add 2 to 3 parts by volume of clean, dry silica sand to 1 part mixed EPIWELD® 580. For proper strength development all components should be at temperatures of 50°F (10°C) and rising. Additional aggregate may be added (up to 5 parts sand to 1 part mixed epoxy). To avoid air entrapment, placement of grout mixes should be made from only one side of work area.

Anchoring Bolts, Rebar, Dowels, and Pins

Used as neat epoxy. For efficient transfer of stress, the hole should be no greater in diameter than 1/4-inch (6.4mm) larger than the bolt, rebar, dowel, pin to be embedded. Depth of embedment is 10 to 15 times the bolt, rebar, etc. diameter. EPIWELD® 580 could be mixed with fine dry silica sand (40/140) at a 1 to 1 ratio for further economy and to increase the modulus of elasticity.

Hole Preparation

Holes should be clean and free of debris. Air or water flushed rotary percussive drilling equipment is recommended. Holes should be brushed with a nylon or wire brush to dislodge drilling debris. Use compressed air to clean out the hole. Diamond drilled holes are not recommended as they do not provide a rough hole profile which establishes the epoxy anchorage. Concrete should be 28 days or older.

Bolt Placement

After placing EPIWELD® 580 in the hole, insert the bolt, rebar, etc. with a twist action for maximum contact between EPIWELD® 580 and hardware and expulsion of any air voids. Position hardware with wedges, jigs, etc. until initial cure. For horizontal or overhead installations use Lambert's EPIWELD® 560 or EPIWELD® 9-N-11.

Patching Compound

After mixing parts A & B together as per instructions, thoroughly blend the selected aggregate into the mixture. For patches greater than 3/4-inch (19.1mm) in depth, coarse aggregate whose maximum size is 1/3 the thickness of the patch may be mixed with the sand used in the epoxy mortar. Deep patches should be applied in 1-inch (25.4mm) increments with subsequent layers applied after the preceding one has cooled to touch but still tacky. Epoxy to aggregate ratios by volume are generally in the range of 1 part mixed epoxy to 2-3 parts aggregate.

Limitations

EPIWELD® 580 should not be used at temperatures below 40°F (4.4°C) or over 100°F (37.8°C). During cold periods, temperatures should be 40°F (4.4°C) and rising at time of application. New concrete or other materials being bonded should be placed while EPIWELD® 580 is still tacky. If it dries, a fresh coat must be applied. Do not apply to wet, "puddled" areas. To minimize differential shrinkage stress, concrete substrate should be fully cured prior to bonding with EPIWELD® 580. When used as a bonding medium for non-slip surfaces, apply EPIWELD® 580 to a dry or slightly damp substrate and use only dry aggregates. Do not thin EPIWELD® 580.

Technical Data

- Applicable Standards: • ASTM C-881, TYPE I, II, IV, V GRADE 2, CLASS B & C
- Florida D.O.T. Specification Section 926 Epoxy Compounds Type A, B, F-2
- AASHTO-M 235

NEAT EPOXY BINDER		Tensile Properties (ASTM D-638)	14 Days – Tensile Strength 7000 PSI (48.3 MPa) Elongation at Break 1.6%
Mixing Properties	1 part A to 1 part B by Volume	Modulus of Elasticity	3.3 x 105 PSI
Color	Part A Resin	Flexural Properties (ASTM D-790)	14 Days – Tensile Modulus of Elasticity in Bending 4.8 x 105 PSI (0.7 MPa)
	Clear / Amber		
	Part B Hardener	Epoxy Grout Mortar	
Viscosity	Neat Epoxy 40-100 Poise Max	Compressive Strength FL D.O.T. Test	
Pot Life	Neat Epoxy 30 – 60 min	2" x 2" x 2" Cubes – 1 Part Mixed Epoxy, 2 Parts Sand	
Tack Free Time (thin film)	45°F (7.2°C)	Average 3 Cubes @ 3 Days – 11480 PSI (79.2 MPa)	
	75°F (23.9°C)		
	90°F (32.2°C)		
Bond Strength (ASTM C-882)	Hardened to Hardened Concrete		
	2 Days (Moist cure)	1200 PSI (8.3 MPa) Minimum	14 Days (Moist cure) 1600 PSI (11.0 MPa) Minimum
Water Absorption (ASTM D-570)	24 Hours - 0.5% Max		
Compressive Strength (ASTM D-695)	24 hours	3200 PSI (22.1 MPa) @75°F (23.9°C)	3600 PSI (24.8 MPa) @ 90°F (32.2°C)
	3 Days	9100 PSI (63.7 MPa) @ 75°F (23.9°C)	9600 PSI (66.2 MPa) @ 90°F (32.2°C)
	7 Days	10500 PSI (72.4 MPa) @ 75°F (23.9°C)	9600 PSI (66.2 MPa) @ 90°F (32.2°C)

Coverage – Estimated Over Concrete Surfaces

Smooth Surface – 100ft²/gal (2.5m²/L) / Rough Surface – 60ft²/gal (1.5m²/L)

Epoxy +	Aggregate =	Mortar / Grout	Binder & Aggregate	Square Feet	Thickness
1-gal (3.8L)	1-gal (3.8L)	1.6-gal (6.1L)	1-gal (3.8L)	12.8 (1.2m ²)	1/8" (3.2mm)
1-gal (3.8L)	2-gal (7.6L)	2.2-gal (8.3L)	1-gal (3.8L)	8.6 (0.8m ²)	3/16" (4.8mm)
1-gal (3.8L)	3-gal (11.4L)	2.8-gal (10.6L)	1-gal (3.8L)	6.4 (0.6m ²)	¼" (6.4mm)
			1-gal (3.8L)	4.3 (0.4m ²)	3/8" (9.5mm)
			1-gal (3.8L)	3.2 (0.3m ²)	½" (12.7mm)
			1-gal (3.8L)	1.6 (0.15m ²)	~1" (25.4mm)

*1 gallon (3.8L) of Lambert emery aggregate or silica sand weighs approximately 10 to 12 pounds (4.5 to 5.4kg). All above figures will vary slightly according to aggregate mesh size and air.

Clean-Up

Clean all tools and equipment immediately after use with lacquer thinner. Do not allow epoxy to harden on tools or equipment. Soap and hot water may be used in some cases.

First Aid

Avoid breathing possible fumes, mists and vapors that can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective creams is required. If material gets into eyes, flush thoroughly with clean water for (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent-based materials or solvents to keep away from open flame or ignition source.

KEEP OUT OF REACH OF CHILDREN. FOR INDUSTRIAL USE ONLY.