



LAMBCO®

WATERBAN® 75

PRECAST CONCRETE WATERPROOFING COATING

Advantages:

- Application by brush, spray or roller
- Single component product; use as is
- Non-flammable
- Asbestos-free
- Paintable
- Clean up with soap and water

Packaging:

55 gal (209 L) drum
5 gal (19 L) pail



LAMBERT CORPORATION
20 N. COBURN AVENUE, ORLANDO, FLORIDA 32805
PHONE: (407) 841-2940 TOLL FREE: 800-432-4746
FAX: (407) 839-1890
WEBSITE: <http://www.lambertusa.com>

Revision: August, 2007
Supersedes all previous publications

Product Description

Waterban 75 is a single-component, non-flammable, asbestos-free, polymer-modified asphalt-emulsion waterproof coating. Waterban 75 can be applied by spray, brush, or roll. Coating is designed to waterproof surfaces of precast concrete and cast-in-place concrete walls that need to be protected from corrosion and environmental elements. It achieves excellent durability, flexibility, and is quick-drying and paintable.

Application

This material should be protected from rainfall and wet conditions until it has cured. Application temperatures should be 50-deg.F and rising. This material should be thoroughly mixed before using. Waterban 75 should be spray-, brush-, or roller-applied to a surface that is free from all dust, dirt, grease or any other foreign matter that may interfere with the bond to the surface. Dry and dusty surfaces should be hosed down or mopped clean with water. Use "as is"; do not thin or dilute. Apply at the specified rate of application. A 2nd coat can be applied while the first coat is still "tacky".

Coverage

Undiluted, coverage is 250-350 square feet per gallon.

Limitations

DO NOT ALLOW material to freeze. DO NOT THIN material. Curing time is approximately 1-hour after application. The information presented herein is to assist users in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents.

Storage

Waterban 75 must be kept from freezing. Shelf-life is 12-months in unopened containers.

HMIS RATINGS			
Health	1	Reactivity	0
Flammable	0	Personal Protection	A

Warnings

Harmful or fatal if swallowed. Harmful to eyes and irritant to skin. Do not get in eyes, on skin or on clothing. Wear eye protection, gloves and protective clothing when handling. Keep out of sewers and water courses and advise authorities if unable to do so.

Disposal

Allow empty containers dry completely and crush containers prior to disposal. Dispose of empty containers in accordance with local authorities and landfill regulations. Do not re-use or recycle containers.

First Aid

If swallowed, do not induce vomiting. Get medical attention immediately. In case of eye contact, immediately flush with plenty of water for at least 15 minutes. Get medical attention immediately. In case of skin contact, wash with soap and cool water. If irritation or redness persists, get medical attention. In case of breathing difficulties or light-headedness, get fresh air and medical attention immediately. Wash contaminated clothing before re-use. Do not place clothing directly in clothes washing machines.

SPECIFICATIONS:

Density (Weight per Gal.):	7.9-8.4 lbs.
Nonvolatile %, ASTM D-2939	45.0-55.0
Viscosity @ 77°F, ASTM D-562 (Kreb's Stormer Unit)	55-65 KU
Softening Point (0°F), ASTM D-36	170-180
Penetration (0.1 mm), ASTM D-5	20-40
Std. Spec. for Emulsified Asphalt AASHTO Designation M-140 ASTM Designation D-997	meets spec meets spec
Resistance to water, ASTM D-2939	no blistering, no loss of adhesion, no re-emulsification
Dry Time, ASTM D-2939	Less than 1 hour
Shelf Life	1 year

Warranty Notice

DISCLAIMER OF WARRANTIES AND LIMITATION OF LIABILITY: LAMBERT CORPORATION, (Seller) warrants that if any goods supplied prove defective in workmanship or material, that Seller shall replace them or refund their purchase price. THIS WARRANTY IS MADE IN LIEU OF ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND/OR FITNESS WHICH ARE HEREBY

DISCLAIMED. IT IS UNDERSTOOD AND AGREED THAT BUYER'S SOLE REMEDY, AND THEREFORE SELLER'S LIABILITY, WHETHER IN CONTRACT, TORT, UNDER ANY WARRANTY, IN NEGLIGENCE, OR OTHERWISE SHALL BE LIMITED TO THE RETURN OF THE PURCHASE PRICE PAID BY PURCHASER OR REPLACEMENT OF ANY DEFECTIVE GOODS SOLD BY SELLER AND UNDER NO CIRCUMSTANCES SHALL SELLER BE LIABLE FOR SPECIAL, INDIRECT OR CONSEQUENTIAL DAMAGES. THE PRICE STATED FOR THE GOODS IS A CONSIDERATION IN LIMITING SELLER'S LIABILITY. Any liability or risk resulting from the use of this product is assumed by the PURCHASER/USER except where a specific warranty is provided by the manufacturer in writing. Before application, the PURCHASER/USER shall determine the suitability of the product for his intended use and PURCHASER/USER assumes all liabilities and risks whatsoever in connection therewith. The terms of this WARRANTY NOTICE may not be orally modified. **THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE FACE HEREOF.**

Product Liability

LAMBERT products are designed to be used in the construction industry and should be applied by competent persons in accordance with current published instructions. Technical advice and recommendations as to the suitability of product for any particular use are made in good faith. However, we have no control over the conditions under which our products are transported to, stored, handled or used by the customer. We cannot be held responsible for difficulty caused by other materials and conditions, or by inferior workmanship. LAMBERT recommends that the customer satisfy themselves as to the product's actual suitability for its intended purpose.

LAMBERT reserves the right to have the true cause of any difficulty determined by accepted test methods by an independent party. Any claim regarding product defect must be received in writing within one year from day of shipment. No claim will be considered without such written notice or after the specified time interval.